



Dalian Richfortune Chemicals Co., Ltd.

12A-11 Yangguang Shuma Building, 596 Huang Pu Road,
DaLian, Liaoning 116023, China

Tel: +86-411-84820922/84821539


Fax: +86-411-84821380

Website: www.richfortunechem.com

Rubber Accelerators TDEC

Chemical Name: Tellurium Diethyl Dithiocarbamate

Structural Formula:



Details:

CAS No: 20941-65-5

Packaging: 25kg plastic woven bag, paper with plastic film bag, 25kg drum.

Molecular Formula: $\text{C}_{20}\text{H}_{40}\text{N}_4\text{S}_8\text{Te}$

Molecular Weight: 721

Specifications:

Item	Powder	Oiled powder
Appearance	Yellow powder	
Initial M.P. $\geq$	105.0	105.0
Loss on drying % $\leq$	0.50	0.50
Zinc content %	16.5-19.0	16.5-19.0
Residue on 150 μm sieve % $\leq$	0.10	0.10
Residue on 63 μm sieve % $\leq$	0.50	0.50
Additive %	\	0.1-2.0

Properties: Soluble in chloroform, benzene and carbon disulfide, slightly soluble in alcohol and gasoline, insoluble in water.



Dalian Richfortune Chemicals Co., Ltd.

12A-11 Yangguang Shuma Building, 596 Huang Pu Road,
DaLian, Liaoning 116023, China

Tel: +86-411-84820922/84821539

Fax: +86-411-84821380

Website: www.richfortunechem.com

Used: Super accelerator of natural rubber, styrene-butadiene rubber. In general, using with some other kinds of accelerators such as benzothiazole, sulfenamide. Used to making inner tube of tires, soft tube, isolating layer of wire and cable, etc.

Storage Notes: Stored in the dry and cooling place with good ventilation, avoid direct to sunlight.

The validity is 1 year.